

# Irradiation test of Silicon detectors with 7-10 MeV protons

- First results -

D.Bechevet<sup>a</sup>, M.Glaser<sup>b</sup>, A.Houdayer<sup>a</sup>, C.Lebel<sup>a</sup>,  
C.Leroy<sup>a</sup>, F.Marullo<sup>a</sup>, M.Moll<sup>a</sup>, P.Roy<sup>b</sup>

<sup>a</sup> Universite de Montreal, Montreal(Quebec), Canada

<sup>b</sup> CERN EP, Geneva Switzerland

RD48/ROSE Collaboration



Most measurements performed by **Patrick Roy**, who can not be here  
because he is having the Defense of his thesis today (Good luck !)

# Material / Diodes / Irradiation

- Wacker silicon
- Orientation:  $\langle 100 \rangle$
- Resistivity:  $2 \text{ K}\Omega\text{cm}$
- Diode producer: ST Microelectronics - ROSE mask
- No oxygen enrichment  
SIMS ( $150\mu\text{m}$ )  $\Rightarrow [\text{O}] = 9 \times 10^{15}\text{cm}^{-3}$ ,  $[\text{C}] < 3 \times 10^{15}\text{cm}^{-3}$
- Irradiation with 7, 8, 9, 10 MeV protons
- Fluence range:  $1 \times 10^{10} \text{ p/cm}^2$  to  $5 \times 10^{13} \text{ p/cm}^2$   
(all given fluences not normalized to NIEL)
- Measurements: IV, CV, annealing at  $80^\circ\text{C}$   
DLTS (see talk of Martin Kuhnke)
- Goal: Does NIEL work for low energy protons ?  
- “Very high ratio of point defects to clusters” -



# Increase of Leakage Current

- Leakage Current measured at full depletion directly after irradiation (left) and after annealing of 4min at 80°C (right)



# $\alpha$ -value

- $\alpha$ -value for 9 MeV protons measured directly after irradiation (left) and after annealing of 4min at 80°C (right)



# $\alpha$ -value - Hardness factor



- Leakage Current measured at full depletion (preliminary data)

Energy / Particle	$\alpha$ (after irradi.) [ $10^{-17}$ A/cm]	$\alpha$ (4 min 80°C) [ $10^{-17}$ A/cm]	hardness factor (leakage current)	hardness factor (damage function) D(E)/95 MeVmb
7 MeV proton	21.4	17.2	3.8	5.3
8 MeV proton	16.9	13.2	2.9	4.8
9 MeV proton	17.4	13.3	2.9	4.3
10 MeV proton	16.1	11.2	2.5	4.0
23 GeV proton		2.68	0.6	$\approx 0.5$
1 MeV neutron (used as reference)		4.56 (reference)	1 (reference)	1 (95 MeVmb)

- $\alpha$ -value does not scale with NIEL for low energy protons  
( $\alpha$ -value measured for 1MeV neutrons was taken as reference)
- $\alpha$ -value 30 to 40% smaller than expected from NIEL

# Change of effective doping concentration

- Effective doping concentration measured directly after irradiation (left) and after annealing of 4min at 80°C (right)



# Damage parameters for $\Delta N_{\text{eff}}$



- Parameters extracted from fit to data

Energy / Particle	$N_d$ [ $10^{11}\text{cm}^{-3}$ ]	$\beta$ [ $10^{-2}\text{cm}^{-1}$ ]	$c$ [ $10^{-14}\text{cm}^2$ ]	hardness factor $\kappa$ determined from $\beta$	hardness factor (damage function) $D(E)/95\text{ MeVmb}$	hardness factor (leakage current)
7 MeV proton	18.4	4.80	19.3	5.2	5.3	3.8
8 MeV proton	18.4	4.27	17.2	4.7	4.8	2.9
9 MeV proton	18.6	4.35	17.0	4.7	4.3	2.9
10 MeV proton	18.3	(4.3)	(13.6)	4.7	4.0	2.5
1 MeV neutron (used as reference)		0.55		reference with $\kappa = 0.6$		0.6

- $\beta$ -value scales with NIEL for low energy protons  
( $\beta$ -value measured for 24GeV/c protons was taken as reference)

# Change of effective doping concentration

- Annealing of depletion voltage / effective doping concentration



- Fluence:  $3.0 \times 10^{13} \text{ p/cm}^2$  for 7,8,9,10 MeV protons  
 $4.9 \times 10^{13} \text{ p/cm}^2$  for 24 GeV/c protons



# Damage parameter $g_y$ (reverse annealing)

- Parameter extracted from fit to data

Energy / Particle	$g_y$ [cm <sup>-1</sup> ]	hardness factor $\kappa$ determined from $g_y$	hardness factor (damage function) D(E)/95 MeVmb	hardness factor $\kappa$ determined from $\beta$	hardness factor (leakage current)
7 MeV proton	0.23	5.7	5.3	5.2	3.8
8 MeV proton	0.20	4.9	4.8	4.7	2.9
9 MeV proton	0.18	4.5	4.3	4.7	2.9
23 GeV protons (used as reference)	0.04	reference with $\kappa = 0.6$			

- $g_y$  scales with NIEL for low energy protons  
(  $g_y$  measured for 24GeV/c protons was taken as reference)

# Conclusions

- Extraction of damage parameters for standard material irradiated with low energy protons
- $\alpha$ -value does not scale with NIEL for low energy protons (7-10 MeV)  
(if  $\alpha$ -value for 1MeV neutrons is taken as reference)  
measured values too low by about 30-40 %
- Damage parameters  $\beta$  and  $g_y$  do  
scale with the NIEL for low energy protons (7-10 MeV)